

## MOTIP Deco Lacquer

Ord.-no.: look at ordering information

## Technical Information



The MoTip Deco Paint assortment is a high quality alkyd lacquer to embellish and repair all kind of objects in and around the house. The MoTip Deco Paint assortment consists of primer, several RAL-lacquers and clear lacquer in aerosols of 400 ml and 150 ml and a brush can of 100 ml.

### Quality & properties

- Excellent coverage and filling property
- Lasting colour and gloss
- Resistant to petrol, chemicals and weather influenc
- Corrosion preventive
- Excellent adhesion

### Physical & chemical data

- Base: Alkyd resin
- Colourname:
  - ◊ carmine red
  - ◊ pure orange
  - ◊ yellow green
  - ◊ oyster white
  - ◊ light ivory
  - ◊ wine red
  - ◊ gold yellow
  - ◊ grey beige
  - ◊ ruby red
  - ◊ traffic white
  - ◊ dear brown
  - ◊ steel blue
  - ◊ fir green
  - ◊ erica violet
  - ◊ turquoise blue
  - ◊ blue lilac
  - ◊ deep black
  - ◊ moss green
  - ◊ pastel orange
  - ◊ light blue
  - ◊ blood orange
  - ◊ ultramarine blue
  - ◊ reseda green
  - ◊ silver grey
  - ◊ blue grey
  - ◊ light grey
  - ◊ chocolate brown
  - ◊ cream white
  - ◊ grey white
  - ◊ grey aluminium
  - ◊ pure white
  - ◊ sky blue
  - ◊ rape yellow
  - ◊ flame red
  - ◊ white aluminum metallic
  - ◊ gentian blue
  - ◊ leaves green
- Degree of gloss:
  - ◊ high gloss, >85 GU
  - ◊ semi mat, 25 ±5 GU
  - ◊ mat, 10 ±2 GU
- Efficiency:
  - ◊ 400 ML – 1,25 - 1,75 m<sup>2</sup>
  - ◊ 150 ML – 0,5 m<sup>2</sup>

- Dry to touch: 3 - 4 h
- Dust dry: 30 - 60 min
- Completely dry: 24 h
- Overcoatable: 24 h
- Surfaces: wood, metal, aluminium, glass, stone and various types of plastic
- Minimum Working Temperature: 15 °C
- Maximum Working Temperature: 25 °C
- Vapour pressure:
  - ◊ 8300/20 bar
  - ◊ 3500/20 bar
- Flash point: n.a. °C
- Temperature Resistance: – 110 °C
- Storage stability: 10 y
- Content:
  - ◊ 400 ML
  - ◊ 150 ML

---

## How to use

- The surface should be clean, dry and free of grease. Remove loose old lacquer and rust and sand the surface. Apply a layer of MoTip primer suitable for the surface. After drying, sand the base layer (grain 600).
- The aerosol should have room temperature. Best processing temperature 15 to 25°C. Before use, shake the aerosol for 2 minutes and spray a sample. Distance to the surface to be treated approximately 25 to 30 centimetre.
- Apply the lacquer in several thin layers. Before applying the next layer, again shake the aerosol. Even when the lacquer has hardened, do not treat with acrylic lacquer or nitro-cellulose lacquer.
- After use, clean the valve (turn aerosol upside down and press the nozzle for approximately 5 seconds).
- The drying time depends on the ambient temperature, the humidity of the air and the thickness of the lacquer applied.

### Environmentally sound

European Aerosols is committed to apply formulations without restricted or critical ingredients and to achieve best possible performance. The caps and packagings are made of recyclable material.

### Disposal

Only the completely emptied cans should be put into the recycling skip or appropriate container for reclaimable refuse. Cans which are not empty should be disposed off as "special refuse".

### Marking/Labelling

All products made by European Aerosols comply with the actual labelling regulations according to Preparation Guideline 1999/45/EG. All aerosols correspond to TRGS 200 and TRG 300 as well as to aerosol guideline 75/324/EWG in the actually valid version.

For any further technical questions call our hotline +31 (0) 561 69 44 00 from Monday to Thursday from 9 h a.m. to 3 h p.m. or on Friday until 12 h p.m.

**As of May 7, 2022** – This release replaces all eventually earlier issued versions.

European Aerosols GmbH, Kurt-Vogelsang-Straße 6, 74855 Haßmersheim - [info-de@european-aerosols.com](mailto:info-de@european-aerosols.com)  
European Aerosols B.V., Wolfraamweg 2, NL-8471 XC Wolvega - [info-nl@european-aerosols.com](mailto:info-nl@european-aerosols.com)