

PRODUCT DATA HARD HAT® AEROSOLS BRIGHT GALVANIZING 2117

DESCRIPTION

RUST-OLEUM® Hard Hat Aerosols Zinc Aluminium Spray Bright Galvanizing 2117 is a fast drying zinc rich primer/topcoat based on an epoxy ester resin. The product contains pure zinc and aluminium as pigment and provides cathodic protection.

RECOMMENDED USES

RUST-OLEUM Zinc Aluminium Spray 2117 should be used on damaged galvanized steel surfaces.

RUST-OLEUM Zinc Aluminium Spray 2117 is intended to be applied on small areas or for touch-up.

RUST-OLEUM Zinc Aluminium Spray 2117 should be used as a single coat in light industrial exposures, corrosive environments and high humidity areas.

TECHNICAL DATA

Appearance:	Flat
Colour:	Aluminium
Propellant:	Dimethyl ether
Recommended film thickness:	35 µm dry, equals 115 µm wet
VOC-content:	647 g/l

Drying times	20°C/50% r.v.
To touch:	20 minutes
To handle:	60 minutes
To recoat:	Within 2 hours or after 48 hours
Full hardness	7 days

Heat resistance: 450°C (dry heat)

Coverage

Theoretical: 1.2 m² per spay can at 35 µm dry

Practical: Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

SURFACE PREPARATION

Remove dirt, grease, oil, loose rust and all other surface contaminants by appropriate means. The surface must be clean and dry during application.

DIRECTION FOR USE

Remove cover cap. Shake vigorously for at least one minute after the rattle of mixing ball is heard. Shake frequently during use.

Hold can approx. 25 cm from surface. Use back and forth motion keeping can parallel with surface. Ensure that can is in motion when spray button is pressed to avoid runs and sags.

Apply a full, wet coat to achieve a close, dense coating film, avoid dry spray.

After use turn can upside down and press spray button for 2 - 3 seconds to clean valve.

APPLICATION CONDITIONS

For good results the relative humidity shall be below 85% and the temperature of the can and substrate above 0°C.

REMARKS

Both products are lead- and chromate free thus eliminating the danger of poisonous gases escaping if the coated surface needs to be welded at a later date.

Andrews Coatings Ltd
Carver Building
Littles Lane
Wolverhampton
West Midlands
WV1 1JY

Tel. 01902 429190

info@rustoleumdirect.co.uk
www.rustoleumdirect.co.uk

PRODUCT DATA **HARD HAT® AEROSOLS BRIGHT GALVANIZING 2117**

SAFETY

Consult Safety Data Sheet and Safety Information printed on the can.

SHELLIFE / STORAGE CONDITIONS

3 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Andrews Coatings Ltd
Carver Building
Littles Lane
Wolverhampton
West Midlands
WV1 1JY

Tel. 01902 429190

info@rustoleumdirect.co.uk
www.rustoleumdirect.co.uk